

Durethan BKV 30 H1.0 000000

Durethan B (PA 6) Glass fiber reinforced / Standard injection moulding grade PA 6, injection molding grade, 30 % glass fibers, heat-stabilized

ISO Shortname ISO 1874-PA 6,MHR,14-100,GF30

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Rheological properties					
C Melt volume-flow rate	260 °C; 5 kg	cm ³ /(10 min)	ISO 1133	14	
Molding shrinkage, parallel	150x105x3; 280 °C / MT 80 °C; 500 bar	%	acc. ISO 2577	0.16	
Molding shrinkage, normal	150x105x3; 280 °C / MT 80 °C; 500 bar	%	acc. ISO 2577	0.82	
Post- shrinkage, parallel	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.03	
Post- shrinkage, normal	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.12	
Mechanical properties (23 °C/50 % r.h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	9800	6100
C Stress at break	5 mm/min	MPa	ISO 527-1,-2	180	105
C Strain at break	5 mm/min	%	ISO 527-1,-2	3.0	6.0
C Tensile creep modulus	1 h	MPa	ISO 899-1		5100
C Tensile creep modulus	1000 h	MPa	ISO 899-1		4100
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	80	95
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	70	70
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	15	20
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	10	10
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	15	20
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	10	10
Flexural modulus	2 mm/min	MPa	ISO 178	8600	5100
Flexural strength	2 mm/min	MPa	ISO 178	280	170
Flexural strain at flexural strength	2 mm/min	%	ISO 178	4.0	6.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178		145
C Puncture energy	23 °C	J	ISO 6603-2	8	14
C Puncture energy	-30 °C	J	ISO 6603-2	6	5
Ball indentation hardness		N/mm ²	ISO 2039-1	210	100
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	222	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	-200	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	-215	
C Temperature of deflection under load	8.00 MPa	°C	ISO 75-1,-2	-110	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	> 200	
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.2	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.8	
C Burning behavior UL 94 (1.6 mm)	1.6 mm	Class	UL 94	HB	
C Burning behavior UL 94	3.2 mm	Class	UL 94	HB	
C Oxygen index	Method A	%	ISO 4589-2	22	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	600	
Thermal conductivity	23 °C	W/(m·K)	ISO 8302	0.3	
Specific heat	23 °C	kJ/(kg·K)	-	1.0	
Temperature index (Tensile strength)	5000 h	°C	IEC 60216-1	170	
Temperature index (Tensile strength)	20000 h	°C	IEC 60216-1	145	
Halving interval (Tensile strength)		°C	IEC 60216-1	8.3	
Relative temperature index (Tensile strength)		°C	UL 746 B	130	
Temperature index (Tensile impact strength)	5000 h	°C	IEC 60216-1	125	
Temperature index (Tensile impact strength)	20000 h	°C	IEC 60216-1	105	
Halving interval (Tensile impact strength)		°C	IEC 60216-1	9.3	
Relative temperature index (Tensile impact strength)		°C	UL 746 B	95	
Temperature index (Electric strength)	5000 h	°C	IEC 60216-1	165	
Temperature index (Electric strength)	20000 h	°C	IEC 60216-1	145	
Halving interval (Electric strength)		°C	IEC 60216-1	11.9	
Relative temperature index (Electric strength)		°C	UL 746 B	120	
Burning rate (US-FMVSS)		mm/min	ISO 3795	passed	

Durethan BKV 30 H1.0 000000

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Electrical properties (23 °C/50 % r.h.)					
C	Relative permittivity	100 Hz	-	IEC 60250	4.3 12
C	Relative permittivity	1 MHz	-	IEC 60250	3.8 4.0
C	Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	110 2350
C	Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	180 750
C	Volume resistivity		Ohm·m	IEC 60093	1E13 1E09
C	Surface resistivity		Ohm	IEC 60093	1E15 1E13
C	Electric strength	1 mm	kV/mm	IEC 60243-1	40 35
C	Comparative tracking index CTI	Solution A	Rating	IEC 60112	475 - 0.6
	Comparative tracking index CTI M	Solution B	Rating	IEC 60112	300 (250) M - 1.2
	Electrolytic corrosion		Rating	IEC 60426	A/B 3
Other properties (23 °C)					
C	Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	~7.0
C	Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	~2.1
C	Density		kg/m ³	ISO 1183	1360
	Glass fiber / glass bead / filler content		%	ISO 3451-1	30
	Bulk density		kg/m ³	ISO 60	~700
Processing conditions for test specimens					
C	Injection molding-Melt temperature		°C	ISO 294	280
C	Injection molding-Mold temperature		°C	ISO 294	80
C	Injection molding-Injection velocity		mm/s	ISO 294	200

Durethan BKV 30 H1.0 000000

Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Publisher: Business Development Plastics

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com